



APET SHEET BT807 SPECIFICATION

| PROPERTIES | METHOD | UNIT | SPEC. |
|---|-------------|--------------------|----------|
| 外觀(Appearance)* | --- | --- | None |
| 寬度(Width) | --- | mm | 0~+5 |
| 厚度(Thickness) | --- | % | ±5% |
| 厚度 CV% (Thickness CV%) | --- | % | ≤ 2.0 |
| 衝擊強度(Impact) | ASTM-1709 | g/mm | ≥ 1650 |
| 引伸模數(Tensile Modulus) | ASTM D-638 | Kg/cm ² | ≥ 16000 |
| 伸長率@屈服點 (Tensile Elongation @ Yield) | ASTM D-638 | % | ≥ 3.5 |
| 屈服點@拉力強度 (Tensile Strength @ Yield) | ASTM D-638 | Kg/cm ² | ≥ 450 |
| 霧度(Haze) | ASTM D-1003 | % | ≤ 3.0 |
| 生產厚度(Specification Thickness) | @Hsinpu | mm | 0.2~1.8 |
| 生產寬度(Specification Width) | @Hsinpu | mm | 500~1200 |

*Note : Fish eye(>0.5mm) / Black Mark (>0.5mm) / Paste Mark/ Flow Mark/ Water Wave/ Press Sludge/ Oil Sludge/ Pin Hole/ Roll/ Wave Edge